

# IntraCon

Crystalline Waterproofing Material



## DESCRIPTION

IntraCon is a cement-based, crystalline waterproofing material used to waterproof, protect, and repair above-grade and below-grade concrete. IntraCon's unique formulation prevents liquid penetration by creating a non-soluble physical barrier over the concrete. IntraCon is recommended for any concrete structure, especially foundations, swimming pools and underground structures.

## FEATURES/BENEFITS

- Waterproofs interior, exterior, above & below grade masonry & concrete surfaces.
- Deeply penetrates to seal pores, capillaries, and shrinkage cracks.
- Resists toxic chemicals and hydrostatic pressure.
- Applicable to positive or negative side of concrete.

## APPLICATION

**Surface Preparation:** The surface must be structurally sound, clean and free of dirt, release agent, efflorescence, curing compounds, laitance, and other contaminants. Remove form marks and other protrusions to prevent "show through". Surface must have an open capillary system to provide grip for the IntraCon. If concrete has a smooth finish sandblasting is recommended to lightly roughen the concrete surface. Repair all surface defects with IntraCon mixed to a mortar consistency. Allow to dry for 10 minutes. IntraCon requires a water saturated surface during application. Wet concrete surface thoroughly with potable water, and remove excess water (ponding) before IntraCon is applied. It is essential that the concrete surface does not dry before IntraCon is applied if concrete surface does dry rewet the area.

**Mixing:** Mix IntraCon with potable water to reach a thin cake batter consistency. Recommended ratios for brush application is 5 parts powder to 2 parts water. For spray application use 5 parts powder to 3 parts water. IntraCon needs to be applied within 20 minutes after mixing.

**For patching or repair applications use 19% of water/50 lbs bag of IntraCon results.**

**Placement:** If IntraCon is being applied by a hand brush or broom make sure Nylon bristles are used. Apply a thin uniform thick coating no thicker than 1/16<sup>th</sup> of an inch. If the project requires a second coat of IntraCon wait until the first coat has set before applying the second. A second coat should not be applied after a time period of 2 days. IntraCon should not be applied in rainy or cold conditions (below 40°F).

**Application:** A fine tip sprayer should be used to lightly wet the surface of the IntraCon once it has set. Typically the surface should be wetted with water multiple times a day. In cases of high temperatures, winds and low humidity more applications will be necessary. IntraCon must be protected from weather and cold subzero temperatures as during the first 48 hours. No covering should be in contact with the surface of the IntraCon during this time as well. If the structure is used to retain a liquid a curing length of 3 days is required and two weeks should pass before the structure is required to hold liquid.

## PACKAGING

IntraCon is available in 50lb pails and 50 lb bags. Coverage: 6 to 7.1 sq ft/lb

## CLEAN UP

Tools and equipment may be cleaned with water before IntraCon hardens or SpecBlast if IntraCon hardens.

## SHELF LIFE

Shelf life of unopened bags stored in a dry facility is 12 months. Excessive temperature differential and/or high humidity can shorten the shelf life expectancy. Store in a cool, dry area away from direct sunlight.

## LIMITATIONS/PRECAUTIONS

Do not retemper after initial mixing. Do not add other cements or additives to this product. IntraCon is a fast setting product, so mixing equipment should be cleaned with water as soon as possible.

Do not allow repairs to freeze until the material has reached a minimum of 1000 psi compressive strength.

In adverse temperatures, follow ACI recommendations for hot/cold weather concreting practices. Use only potable water for mixing. Minimum surface and ambient temperature of 45°F and rising is required at the time of application. For optimum results, condition material to between 65°F and 85°F.

**SPEC CHEM**  
Solution to Service

1511 Baltimore Ave, Suite 600  
Kansas City, MO 64108

[www.specchemllc.com](http://www.specchemllc.com)

866.791.8700

## LIMITATIONS/PRECAUTIONS

**Caution:** Contains Portland Cement and sand. Cement will cause irritation. Avoid contact. A dust respirator, safety goggles, and rubber gloves are recommended. Avoid prolonged contact with clothing. In case of contact with eyes, immediately flush with water for at least 15 minutes. Get prompt medical attention. Do not wear contact lenses when working with this product. DO NOT take internally. Keep out of reach of children.

Avoid hazards by following all precautions found in the Material Safety Data Sheet (MSDS), product labels, and technical literature. Please read this information prior to using the product.

## WARRANTY

### NOTICE-READ CAREFULLY CONDITIONS OF SALE

SpecChem offers this product for sale subject to and limited by the warranty which may only be varied by written agreement of a duly authorized corporate officer of SpecChem. No other representative of or for SpecChem is authorized to grant any warranty or to waive limitation of liability set forth below.

### WARRANTY LIMITATION

SpecChem warrants this product to be free of manufacturing defects. If the product when purchased was defective and was within use period indicated on container or carton, when used, SpecChem will replace the defective product with new product without charge to the purchaser. SpecChem makes no other warranty, either expressed or implied, concerning this product. There is no warranty of merchantability. NO CLAIM OF ANY KIND SHALL BE GREATER THAN THE PURCHASE PRICE OF THE PRODUCT IN RESPECT OF WHICH DAMAGES ARE CLAIMED.

### INHERENT RISK

Purchaser assumes all risk associated with the use or application of the product.



1511 Baltimore Ave, Suite 600  
Kansas City, MO 64108

[www.specchemllc.com](http://www.specchemllc.com)

866.791.8700