

# TOTAL PATCH



Very rapid setting multi-purpose concrete repair mortar

## DESCRIPTION

TOTAL PATCH is a very rapid-setting, multi-purpose, rapid-setting concrete repair mortar for use on concrete floors, highway pavements, and other applications requiring high early strength and early resumption of traffic or use.

TOTAL PATCH is formulated to meet the requirements of ASTM C928 Packaged, Dry, Rapid Hardening Cementitious Material for Concrete Repair and AASHTO T260. TOTAL PATCH incorporates the latest technology offering superior durability, performance and ease of application without liquid activators for horizontal (featheredge to 4") and vertical form & pour applications.

## FEATURES/BENEFITS

- One-component, dry-polymer, Just add water.
- Easy-to-use, flowable consistency
- Air entrained for excellent freeze-thaw durability
- Suitable for horizontal and formed vertical application
- Takes traffic in 1 hour after set (at 73°F)
- Feather edge to 4" without extension

## APPLICATION

**Surface Preparation:** The concrete must be sound and free of all foreign material, including oil, grease, dust, laitance or other surface contaminants. For maximum durability, saw cut the perimeter of the repair 1/8" deeper than the depth of the repair, creating a notched, reinforced edge. Mechanically abrade the surface by an engineered approved method in accordance with ICRI 310.2 Guideline to a minimum CSP 6. **All concrete surfaces to be repaired must be in a saturated-surface-damp (SSD) condition with no standing water on the surface.**

**Priming/Scrub Coat:** Thoroughly clean all exposed steel reinforcing of rust and coat with **SpecPrep SB**.

**Prepared concrete must be SSD** and primed with a spray or brush coat of **SpecPrep SB** and the repair mortar applied wet on wet or up to the recommended open time (see **SpecPrep SB** technical data sheet).

As an alternative, apply a scrub coat of the properly mixed repair mortar by scrubbing a thin layer into the pre-dampened substrate with a stiff brush. Place the repair mortar immediately before the bond coat dries.

**Mix 7.0– 9.0 pints (depending on desired consistency) of clean water per 50 pound bag of material.** Mix with a low speed drill or mortar mixer. Add recommended amount of clean water into the container, followed by slowly adding the TOTAL PATCH powder. For non-DOT applications, up to 9.0 pints can be used for greater flow. Mix 2-3 minutes. Mix only what can be applied within the setting period.

## APPLICATION (con't)

Depending on the application and area dimensions, TOTAL PATCH can be applied in applications from a feather edge to 4" without extension. Consult SpecChem tech service for further details.

**Deep Applications:** For DOT and heavy traffic applications (roadways, parking structures, etc) over 4", TOTAL PATCH should be extended with clean, SSD, 3/8" aggregate up to 60% by weight (30lbs). Choose a clean (free of organic material) well-graded 3/8" aggregate. Aggregate should be pre-dampened prior to mixing with TOTAL PATCH. The total mixing water for the batch shall be reduced by the amount of free water found in the aggregate. 60% extension will add approx. 0.18 cu-ft to the unit yield. Thoroughly mixed product should be placed within 5-6 min.

**Placement:** Trowel, or screed TOTAL PATCH firmly into the prepared area, ensuring intimate contact with the bonding surface. Finish TOTAL PATCH level with the surrounding concrete and allow to take an initial set. After the initial set, when TOTAL PATCH is surface hard, finish by hand trowelling. Excessive troweling is not required.

## TYPICAL TEST DATA

Test Data based on 9.0 pints (4.5 quarts) water	
<b>Set Time at 70°F (ASTM C-266)</b>	
Initial Set	12 min
Final Set	15 min
<b>Compressive Strength (ASTM C109)</b>	
1 hour	3500 psi
1 day	5400psi
7 days	6200 psi
28 days	7100 psi
<b>Bond Strength (ASTM C882 modified)</b>	
7 days	2245 psi
<b>Flexural Strength (ASTM C348)</b>	
7 days	750 psi
28 days	1150 psi
<b>Length Change (ASTM C157)</b>	
Air Cured	-.04%
Water Cured	+.02%



1511 Baltimore Ave, Suite 600  
Kansas City, MO 64108

www.specchemllc.com 866.791.8700

## APPLICATION (con't)

**Finishing/Curing:** Finish the repair material to the desired texture to best match the surrounding concrete. Do not add additional water to the surface during finishing. Lightly spray **SpecFilm** as a finishing aid on this and any other polymer modified mortars to assist in finishing. Total Patch is self-curing under most conditions.

## SPECIFICATIONS/COMPLIANCE

ASTM C928 (Rapid Hardening Mortar)  
AASHTO T-260

## PACKAGING

- 50 lb bag
  - 3,000 lb SuperSack
- Coverage:** approx 20 sq-ft @ 1/4"

## SHELF LIFE

Shelf life of unopened bags stored in a dry facility is 12 months. Excessive temperature differential and/or high humidity can shorten the shelf life expectancy. Store in a cool, dry area away from direct sunlight.

## LIMITATIONS/PRECAUTIONS

Minimum thickness for horizontal repairs subjected to heavy or severe traffic is 1/2". Do not retemper after initial mixing. Do not add other cements or additives to this product. TOTAL PATCH is a fast setting product, so mixing equipment should be cleaned with water as soon as possible. Use only potable water for mixing.

Application range 40°F to 90°F. Please consult SpecChem for special instructions on any application outside this temperature range.

**Adverse Weather Application:** In adverse temperatures, follow ACI recommendations for hot/cold weather concreting practices. For optimum results, condition bagged material to between 65°F and 85°F overnight.

**Cold Weather** applications should follow procedures outlined in ACI 306. Conditioning the material before mixing to 65°F and 85°F, heating the repair area, using warm water for mixing, and tenting or insulating the patch area after application will increase strength development. Do not use direct, unvented heat on the patch after installation. Do not allow repairs to freeze until the material has reached a minimum of 1000 psi compressive strength.

**Caution:** Contains Portland cement and sand. Cement will cause irritation. Avoid contact. A dust respirator, safety goggles, and rubber gloves are recommended. Avoid prolonged contact with clothing. In case of contact with eyes, immediately flush with water for at least 15 minutes. Get prompt medical attention. Do not wear contact lenses when working with this product. DO NOT take internally. Keep out of reach of children.

Avoid hazards by following all precautions found in the Safety Data Sheet (SDS), product labels, and technical literature. Please read this information prior to using the product.

## CLEAN UP

Tools and equipment may be cleaned with water before TOTAL PATCH hardens.

## WARRANTY

### NOTICE-READ CAREFULLY CONDITIONS OF SALE

SpecChem offers this product for sale subject to and limited by the warranty which may only be varied by written agreement of a duly authorized corporate officer of SpecChem. No other representative of or for SpecChem is authorized to grant any warranty or to waive limitation of liability set forth below.

### WARRANTY LIMITATION

SpecChem warrants this product to be free of manufacturing defects. If the product when purchased was defective and was within use period indicated on container or carton, when used, SpecChem will replace the defective product with new product without charge to the purchaser. SpecChem makes no other warranty, either expressed or implied, concerning this product. There is no warranty of merchantability. NO CLAIM OF ANY KIND SHALL BE GREATER THAN THE PURCHASE PRICE OF THE PRODUCT IN RESPECT OF WHICH DAMAGES ARE CLAIMED.

### INHERENT RISK

Purchaser assumes all risk associated with the use or application of the product.

**SPEC**CHEM   
Solution to Service

1511 Baltimore Ave, Suite 600  
Kansas City, MO 64108  
www.specchemllc.com 866.791.8700